

HIPERSITE W2000 is Polycarbonate plastics which is compounded with Carbon Nano-Tube and has excellent performance about ESD and Cleanliness (Chemical/Physical) characteristics.

ITEM	Measurement Method	Unit	W2000
<b><u>Mechanical Properties</u></b>			
Specific Gravity	ASTM D-792	-	1.26
Tensile Strength	ASTM D-638	MPa	60
Flexural Modulus	ASTM D-790	MPa	2500
Flexural Strength	ASTM D-790	MPa	90
Izod Impact Strength(1/8" notched)	ASTM D-256	J/m	150
Rockwell Hardness	ASTM D-785	R	117
<b><u>Thermal Properties</u></b>			
Temperature of deflection under load-0.45MPa			145
Temperature of deflection under load-1.82MPa	ASTM D-648	°C	132
Coefficient of Linear thermal expansion	ASTM D-696	10 <sup>-5</sup> /K	6.5
<b><u>Cleanliness Properties</u></b>			
Outgassing	HS/GC 85°C 16hrs	µg/g	<0.2
LPC	36KHz 120W 60s(1.0~2.0µm)	count/sq	<50
Ion Contamination			
F			<0.005
Cl			<0.005
Br			<0.005
NO3			<0.005
PO4			<0.005
SO4	DI water 60°C 1hr	µg/g	<0.01
NH4			<0.005
Na			<0.005
K			<0.005
Ca			<0.005
<b><u>Injection Proces Characteristic</u></b>			
Mold Shrinkage	-	%	0.5~0.6
Sylinder Temperature	-	°C	280~320
Mold Temperature	-	°C	60~90
Drying Temperature	-	°C	120
Drying Time	-	hrs	>4

Note: This listed properties are portrayed as general information only and are not product specifications. These numerical values might change for the reasons for the properties improvement etc.